

Datasheet CKX

Composition

Fabric	: Polyester HT fabric	95 gr/m ²
Coating	: One-side, plasticized PVC	<u>270 gr/m²</u>
Thickness	: -	365 gr/m ² ±30

Properties

		Length	Width	
Tensile strength	DIN53354	1200 N/5cm	1000 N/5cm	± 25 %
Elongation	DIN53354	22 %	20 %	± 25 %
Tear strength	DIN53356	75 N	65 N	± 35 %
Adhesion	DIN53357	> 50 N/5cm		
Impermeability to water	DIN53886	> 100 cm		
Colorfastness	ISO 105	>= 7		
Cold resistance	DIN53361	< -30 °C		

Washing instructions



Handwash

Clean with damp piece of cloth and household soap (solvent free).
 Don't fold and put the material away when wet.

Remarks

Small differences in color and gloss are possible (hold recipe numbers separated).
 Reproducibility Color: unicolor < 1, printed < 1.5, dualcolor < 2 (Delta E CIE-lab 1976 D65).
 Translucency is not uniform.

Date: 26/9/2018

Datasheet date: 7/11/2014

ABN AMRO BANK: 47.37.10.978
 IBAN: NL94ABNA0473710978
 BIC: ABNANL2A

ING BANK: 903250
 IBAN: NL45INGB0000903250
 BIC: INGBNL2A

BTW/VAT: NL005840247B01
 Chamber of Commerce: 08036741

Our general terms and conditions are applied to all our offers, orders and agreements. A copy is available on request.



Management
 System
 ISO 9001:2015
 www.tuv.com
 ID 9108622561